



Notes:

- Please refer to all relevant method statements for preparation and application information.
- All Hydroswell BentoStrip must overlap 100mm, side by side where ever there are intersections.
- Slurry to be applied a minimum of 70 mm either side of the Hydroswell BentoStrip.
- Absolute minimum Xypex thickness 200mm, typically 250mm.
- All construction joints must have Hydroswell BentoSteel installed over the top of Hydroswell BentoStrip.

Legend:

- ① --- Xypex Concentrate Slurry
- ② ■ Hydroswell BentoStrip
- ③ ⊕ Hydroswell BF 36/52
- ④ □ Hydroswell BentoSteel
- Concrete containing Xypex Admix

02	Drawing template updated	NG	22/01/24	DW	07/03/24
01	BentoSteel note added	NG	03/10/22	AL	03/10/22
Rev	Description	Drawn by	Date	Checked	Date

All dimensions are in millimetres, unless stated. All dimensions to be checked on site prior to commencement of any work. Copyright protected - no part of this drawing maybe reproduced without prior consent of SMR Projects Ltd.



www.smrxypex.co.uk
e.info@smrxypex.co.uk
t.01295 279747

waterproofing specialists | Hydroswell XYPEX

SMR House, Beaumont Close, Banbury, Oxfordshire, OX161TG

Project Name: **Xypex Standard Detail**

Drawing Title: **Monolithically Poured Split Slab**

Project Number: - Date: 26/09/22

Drawing Number: XSD011 Rev: 02

Drawn: NG	Checked: AL	Approved: AL	Scale: NTS	ISO A4 297 x 210mm
-----------	-------------	--------------	------------	-----------------------